

# Technical Data Sheet

## Alathon M6580



High Density Polyethylene

### Product Description

Alathon M6580 is a narrow molecular weight distribution homopolymer that enhances processing and stiffness, exhibits excellent color, low odor and good processing stability. Typical applications include cases, crates, trays, tote bins and open-head pails.

### Regulatory Status

For regulatory compliance information, see Alathon M6580 [Product Stewardship Bulletin \(PSB\)](#) and [Safety Data Sheet \(SDS\)](#).

<b>Status</b>	Commercial: Active
<b>Availability</b>	North America
<b>Application</b>	Crates; Pallets/Trays/Tote Bins
<b>Market</b>	Rigid Packaging
<b>Processing Method</b>	Injection Molding

Typical Properties	Nominal Value	English Units	Nominal Value	SI Units	Test Method
<b>Physical</b>					
Melt Flow Rate, (190 °C/2.16 kg)	8.2	g/10 min	8.2	g/10 min	ASTM D1238
Density, (23 °C)	0.965	g/cm <sup>3</sup>	0.965	g/cm <sup>3</sup>	ASTM D1505
Bulk Density	33-37	lb/ft <sup>3</sup>	529-593	kg/m <sup>3</sup>	ASTM D1895
Spiral Flow	9.9	in	25.1	cm	LYB Method
<b>Mechanical</b>					
Flexural Modulus					
(1% Secant)	240000	psi	1650	MPa	ASTM D790
(2% Secant)	204000	psi	1410	MPa	ASTM D790
Flexural Young's Modulus	257000	psi	1770	MPa	ASTM D790
Tensile Modulus, (1% Secant)	144000	psi	993	MPa	ASTM D638
Tensile Young's Modulus	180000	psi	1240	MPa	ASTM D638
Tensile Stress at Break, (23 °C)	4500	psi	31.0	MPa	ASTM D638
Tensile Stress at Yield, (23 °C)	4650	psi	32.1	MPa	ASTM D638
Tensile Elongation at Break, (23 °C)	16	%	16	%	ASTM D638
Tensile Elongation at Yield, (23 °C)	7	%	7	%	ASTM D638
<b>Impact</b>					
Notched Izod Impact Strength, (23 °C)	0.68	ft-lb/in	36	J/m	ASTM D256
Unnotched Impact Strength, (-18 °C)	No Break		No Break		ASTM D4812
<b>Hardness</b>					
Shore Hardness, (Shore D, max)	73		73		ASTM D2240
<b>Thermal</b>					
Vicat Softening Temperature	267	°F	131	°C	ASTM D1525
Low Temperature Brittleness, F <sub>50</sub>	-99.0	°F	-72.8	°C	ASTM D746

Deflection Temperature Under Load, (66 psi, Unannealed)	181.0 °F	82.8 °C	ASTM D648
Melting Temperature	272.1 °F	133.4 °C	ASTM D3418
Crystallization Temperature	244.0 °F	117.8 °C	ASTM D3418

## Notes

Conditions of Tensile Stress and Elongation values are: 50 mm/min, Type IV specimen.

Conditions of Flexural Modulus values are: 0.5 inches/min or 12.5 mm/min.

Conditions of Tensile Modulus values are: 50 mm/min, Type I Specimen.

Spiral Flow measures the number of inches of flow produced when molten resin is injected into a long, spiral channel (0.0625" insert), at a constant injection pressure of 1000 psi with a melt temperature of 440 °F.

Deflection Temperature Under Load and Low Temperature Brittleness data are for control and development work and are not intended for use in design or predicting performance at elevated or sub-ambient temperatures.

These are typical property values not to be construed as specification limits.

## Processing Techniques

Specific recommendations for resin type and processing conditions can only be made when the end use, required properties and fabrication equipment are known.

## Company Information

For further information regarding the LyondellBasell company, please visit <http://www.lyb.com/>.

© LyondellBasell Industries Holdings, B.V. 2018

## Disclaimer

Information in this document is accurate to the best of our knowledge at the date of publication. The document is designed to provide users general information for safe handling, use, processing, storage, transportation, disposal and release and does not constitute any warranty or quality specification, either express or implied, including any warranty of merchantability or fitness for any particular purpose. Users shall determine whether the product is suitable for their use and can be used safely and legally.

In addition to any prohibitions of use specifically noted in this document, LyondellBasell may further prohibit or restrict the sale of its products into certain applications. For further information, please contact a LyondellBasell representative.

## Trademarks

The Trademark referenced within the product name is owned or used by the LyondellBasell family of companies.