

# SABIC<sup>®</sup> HDPE P6006

HIGH DENSITY POLYETHYLENE FOR PIPE

## DESCRIPTION

P6006 is black compound high density (class MRS 10 - PE 100) Polyethylene with bimodal distribution of molecular mass. It is specifically designed for pressure Pipe applications. It provides excellent stress crack resistance properties (ESCR) combined with very good long term hydrostatic strength.

## TYPICAL APPLICATIONS

P6006 Pressure pipes for drinking water, irrigation, gas distribution and waste water pipes. It is also recommended for manufacture of chemical liners and containers.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate<sup>(1)</sup></b>			
@ 190°C & 5 kg load <sup>(1)</sup>	0.23	g/10 min	ISO 1133
@ 190°C & 21.6 kg load <sup>(1)</sup>	6.2	g/10 min	ISO 1133
<b>Carbon black content<sup>(1)</sup></b>	2.25	%	ISO 6964
<b>Density at 23°C<sup>(1)</sup></b>	959	kg/m <sup>3</sup>	ASTM D1505
<b>MECHANICAL PROPERTIES</b>			
<b>Tensile Strength at Yield<sup>(2)</sup></b>	23	MPa	ASTM D638
<b>Tensile Elongation at Yield<sup>(2)</sup></b>	9	%	ISO 527-1/-2
<b>Tensile modulus<sup>(2)</sup></b>	900	MPa	ASTM D638
<b>Charpy Impact Notched @ 23°C<sup>(3)</sup></b>	26	kJ/m <sup>2</sup>	ISO 179
<b>Charpy Impact Notched @ -30°C<sup>(3)</sup></b>	13	kJ/m <sup>2</sup>	ISO 179
<b>Hardness (Shore D)<sup>(3)</sup></b>	63	-	ASTM D2240
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Point @ 50N (VST/B)</b>	74	°C	ISO 306
<b>OIT (210°C)</b>	>20	min	EN 728

(1) Typical values: not to be construed as specification limits.

(2) Test specimen according to ISO 527-2 type 1 BA, thickness 2mm with 50mm/min test speed.

(3) Properties are based on 20 m film produced at 4 BUR using 100% P6006.

## PROCESSING CONDITIONS

Typical processing conditions for P6006 Melt temperature: 190-220°C

## FOOD REGULATION

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, available on the Internet ([www.SABIC.com](http://www.SABIC.com)). Additional specific information can be requested via your local Sales Office.



## STORAGE AND HANDLING

Polyethylene material / compound should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably don't exceed 50°C. SABIC would not give warranty to bad storage conditions lead to quality deterioration and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.