

SABIC[®] HDPE FI1 157

HIGH DENSITY POLYETHYLENE

DESCRIPTION

SABIC[®] HDPE FI1 157 is a High Density Polyethylene copolymer grade typically used for blown film applications. It has high molecular weight, broad molecular weight distribution and high density to produce film with low gels level, high stiffness, high melt strength, high impact resistance and with narrow gauge tolerances at low film thickness. SABIC[®] HDPE FI1 157 can be processed at high throughput with good bubble stability.

The product mentioned herein is in particular not tested and therefore not validated for use in pharmaceutical / medical applications

TYPICAL APPLICATIONS

SABIC[®] HDPE FI1 157 is typically used for the production of grocery sacks, shopping bags, refuse bags, liners, bitumen release foils, lamination and paper lamination films, labels, artificial paper, thin films for bag on roll and heavy duty bags.

TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
POLYMER PROPERTIES			
Melt Flow Rate			
at 190 °C and 5 kg	0.35	g/10 min	ISO 1133
at 190 °C and 21.6 kg	11	g/10 min	ISO 1133
Density	957	kg/m ³	ASTM D1505
MECHANICAL PROPERTIES			
Hardness Shore D	62	-	ISO 868
FILM PROPERTIES			
Tensile Properties ⁽¹⁾			
stress at break, MD	50	MPa	ISO 527-3
stress at break, TD	45	MPa	ISO 527-3
strain at break, MD	400	%	ISO 527-3
strain at break, TD	450	%	ISO 527-3
Dart Impact Strength			
F50	240	g	ASTM D1709
Elmendorf Tear Strength			
MD	200	mN	ISO 6383-2
TD	450	mN	ISO 6383-2
THERMAL PROPERTIES			
Vicat Softening Temperature			
at 50 N (VST/B)	75	°C	ISO 306/B
Brittleness Temperature	<-80	°C	ASTM D746

(1) Properties are based on 20 µm film produced at a BUR of 4 using 100% FI1 157.

PROCESSING CONDITIONS

Typical processing conditions for F11157 are:

Melt Temperature: 200 - 225°C.

Frost Line Height: 6 - 8 times die cross-cut.

BUR: 3 – 5

HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Detailed information is provided in the relevant Material Safety Datasheet and or Standard Food Declaration, Additional specific information can be requested via your local Sales Office.

QUALITY

SABIC is fully certified in accordance with the internationally accepted quality standard ISO 9001.

ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PE resin within 6 months after delivery.

DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NON-INFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.