

# SABIC<sup>®</sup> PP 5780P

POLYPROPYLENE HOMOPOLYMER FOR INJECTION MOLDING

## DESCRIPTION

SABIC<sup>®</sup> PP 5780P is a PP homopolymer grade with narrow molecular weight distribution and formulated with slip agent. This grade is suitable for injection molding applications require good flow properties, low COF and good gloss.

## TYPICAL APPLICATIONS

SABIC<sup>®</sup> PP 5780P can be used for household articles, toys, thin-walled packaging, caps & closures items.

## TYPICAL PROPERTY VALUES

Revision 20181012

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
<b>Melt Flow Rate</b>			
at 230°C and 2.16kg	25	g/10 min	ASTM D1238
<b>Density</b>			
at 23°C	905	kg/m <sup>3</sup>	ASTM D792
<b>MECHANICAL PROPERTIES</b>			
<b>Flexural Modulus (1% Secant)<sup>(1)</sup></b>			
	1500	MPa	ASTM D790 A
<b>Izod Impact Strength</b>			
notched, at 23°C	30	J/m	ASTM D256
<b>Rockwell Hardness, R-Scale</b>			
	104	-	ASTM D785
<b>FILM PROPERTIES</b>			
<b>Tensile Properties</b>			
stress at yield	36	MPa	ASTM D638
strain at yield	11	%	ASTM D638
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
	153	°C	ASTM D1525
<b>Heat deflection temperature</b>			
at 455kPa	96	°C	ASTM D648

(1) Based on injection molded specimens

## PROCESSING CONDITIONS

Typical processing conditions for 5780P are:

Barrel temperature range: 200 - 250°C.

Mold shrinkage: 1.2 - 2.5% depending on wall thickness and Processing conditions.

Mold temperature: normally 15 - 40°C, up to 65°C for thick parts.

## HEALTH, SAFETY AND FOOD CONTACT REGULATIONS

Material Safety Data Sheets (MSDS) and Product Safety declarations are available on our Internet site <http://www.SABIC.com>. For additional specific information please contact SABIC local representative.

DISCLAIMER: This product is not intended for and must not be used in any pharmaceutical / medical applications.



## STORAGE AND HANDLING

Polypropylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process PP resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.