

# SABIC® LLDPE 118NJ

LINEAR LOW DENSITY POLYETHYLENE

## DESCRIPTION

SABIC® LLDPE 118NJ is a butene linear low density polyethyleneresin typically used for general purpose applications. Films produced from this resin are tough with good puncture resistance, high tensile strength and good hot tack properties. 118NJ is TNPP free and it does not contain slip and antiblock additive.

## TYPICAL APPLICATIONS

Shipping sacks, ice bags, frozen food bags, stretch wrap film, produce bags, liners, carrier bags, garbage bags, agricultural films, laminated and coextruded films for meat wrap, frozen food and other food packaging, shrink film (for blending with LDPE), industrial consumer packaging, and high clarity film applications if blended with (10 - 20%) LDPE.

## TYPICAL PROPERTY VALUES

Revision 20260304

PROPERTIES	TYPICAL VALUES	UNITS	TEST METHODS
<b>POLYMER PROPERTIES</b>			
Density	918	kg/m <sup>3</sup>	ASTM D1505
<b>Melt Flow Rate (MFR)</b>			
at 190 °C and 2.16 kg	1.0	dg/min	ISO 1133
<b>OPTICAL PROPERTIES <sup>(1)</sup></b>			
Haze <sup>(1)</sup>	13	%	ASTM D1003
Gloss (45°)	50	%	ASTM D2457
<b>FILM PROPERTIES <sup>(1)</sup></b>			
Tear strength MD	40	kN/m	ISO 6383-2
<b>Tensile test film</b>			
Modulus of elasticity MD	160	MPa	ISO 527-3
Stress at break TD	30	MPa	ISO 527-3
Strain at break MD	700	%	ISO 527-3
Strain at break TD	850	%	ISO 527-3
Stress at break MD	37	MPa	ISO 527-3
Modulus of elasticity TD	180	MPa	ISO 527-3
Yield stress TD	11	MPa	ISO 527-3
Tear strength TD	120	kN/m	ISO 6383-2
Impact strength	22	kJ/m	ASTM D4272
<b>THERMAL PROPERTIES</b>			
<b>Vicat Softening Temperature</b>			
at 10 N (VST/A)	100	°C	ISO 306
<b>DSC test</b>			
melting point	121	°C	SABIC method

(1) Properties have been measured by producing 30 µm film with 2.5 BUR using 100% 118NJ.

## ENVIRONMENT AND RECYCLING

The environmental aspects of any packaging material do not only imply waste issues but have to be considered in relation with the use of natural resources, the preservations of foodstuffs, etc. SABIC Europe considers polyethylene to be an environmentally efficient packaging material. Its low specific energy consumption and insignificant emissions to air and water designate polyethylene as the ecological alternative in comparison with the traditional packaging materials. Recycling of packaging materials is supported by SABIC Europe whenever ecological and social benefits are achieved and where a social infrastructure for selective collecting and sorting of packaging is fostered. Whenever 'thermal' recycling of packaging (i.e. incineration with energy recovery) is carried out, polyethylene -with its fairly simple molecular structure and low amount of additives- is considered to be a trouble-free fuel.

## PROCESSING CONDITIONS

Typical processing conditions for 118N1 are:

Melt temperature: 195°C - 215°C, Blow up ratio: 2.0 - 3.0

## STORAGE AND HANDLING

Polyethylene resin should be stored in a manner to prevent a direct exposure to sunlight and/or heat. The storage area should also be dry and preferably do not exceed 50°C. SABIC would not give warranty to bad storage conditions which may lead to quality deterioration such as color change, bad smell and inadequate product performance. It is advisable to process polyethylene resin within 6 months after delivery.

## DISCLAIMER

Any sale by SABIC, its subsidiaries and affiliates (each a "seller"), is made exclusively under seller's standard conditions of sale (available upon request) unless agreed otherwise in writing and signed on behalf of the seller. While the information contained herein is given in good faith, SELLER MAKES NO WARRANTY, EXPRESS OR IMPLIED, INCLUDING MERCHANTABILITY AND NONINFRINGEMENT OF INTELLECTUAL PROPERTY, NOR ASSUMES ANY LIABILITY, DIRECT OR INDIRECT, WITH RESPECT TO THE PERFORMANCE, SUITABILITY OR FITNESS FOR INTENDED USE OR PURPOSE OF THESE PRODUCTS IN ANY APPLICATION. Each customer must determine the suitability of seller materials for the customer's particular use through appropriate testing and analysis. No statement by seller concerning a possible use of any product, service or design is intended, or should be construed, to grant any license under any patent or other intellectual property right.